

PRODUCT DATA SHEET

Sika ViscoFlow[®]-1000

HIGH RANGE WATER REDUCING/SUPERPLASTICISING CONCRETE
ADMIXTURE WITH ENHANCED WORKABILITY RETENTION



PRODUCT DESCRIPTION

Sika ViscoFlow[®]-1000 is a liquid admixture for concrete based on unique polycarboxylate polymers technologies. Sika ViscoFlow[®]-1000 is designed as a high range water reducer or superplasticiser. It is particularly suited for use in concretes that require low water/cement ratios and / or high water reductions with excellent workability retention properties of up to 3 hours.

Sika ViscoFlow[®]-1000 meets the requirements of BS EN 934-2 table.

USES

Sika ViscoFlow[®]-1000 is a unique product that is suitable for the production of ready mixed concrete

- Applications that require extended consistence retention without delayed setting
- Suitability for use across broad range of consistence classes from S3 – SF3
- High performance concrete
- Self compacting concrete
- High rise/pumped concrete
- Slip form concrete
- Improved effectiveness in higher ambient temperatures

CHARACTERISTICS / ADVANTAGES

- High range water reductions resulting in higher strengths and densities
- Extended consistence retention
- Improved cohesion properties
- Improved early and ultimate strengths
- Excellent placement characteristics
- Improved rheology
- Improved durability
- Reduced segregation and bleeding
- Reduced drying shrinkage
- Reduced mix costs

APPROVALS / STANDARDS

Conforms to the requirements of BS EN 934-2 Tables 3.1 & 3.2

DoP 02 13 01 01 100 0 000853 1088, certified by Factory Production Control Body 0086, Certificate 541325, and provided with the CE mark

PRODUCT INFORMATION

Chemical Base	Modified polycarboxylate
Packaging	20 litre, 200 litre, 1000 litre IBC
Appearance / Colour	Clear to slightly hazy liquid
Shelf Life	12 months from date of production if stored properly in undamaged containers.
Storage Conditions	Store in dry conditions at temperatures between +5°C and +25°C. Protect from direct sunlight and frost.

Density	1.075 kg/l (at +20°C)
pH-Value	5.0 +/- 1.0
Total Chloride Ion Content	<0.1% w/w (chloride free)
Equivalent Sodium Oxide	<0.35% w/w

TECHNICAL INFORMATION

Specific Advice	Freezing Point: +1°C Air Entrainment: Negligible, minimal increase Effect on Setting: Extension to normal setting time Effect of Overdosing: Increased workability and segregation
-----------------	---

APPLICATION INFORMATION

Recommended Dosage	0.3 - 0.8% by weight of cement
Compatibility	Sika ViscoFlow®-1000 may be combined with many other Sika products. Important: Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information and advice about any specific combinations.
Dispensing	Sika ViscoFlow®-1000 should be dispensed through suitable calibrated dosing equipment. Sika ViscoFlow®-1000 is added to the gauging water or added with it into the concrete mixer.
Restrictions	<ul style="list-style-type: none"> ▪ When using Sika ViscoFlow®-1000 a suitable mix design has to be taken into account and local material sources shall be trialled. ▪ Sika ViscoFlow®-1000 shall not be added to dry cement. ▪ Excessive water addition or overdosing may cause bleeding or segregation. ▪ Support from our Technical Service Department is recommended. Frost: If frozen and / or if precipitation has occurred, Sika ViscoFlow®-1000 may be used after thawing slowly at room temperature followed by intensive remixing.

APPLICATION INSTRUCTIONS

APPLICATION METHOD / TOOLS

- The standard rules of good concreting practice, concerning production and placing, are to be followed.
- Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components.
- Fresh concrete must be cured properly and curing applied as soon as possible.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always

refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet
Sika ViscoFlow®-1000
April 2019, Version 02.01
021301011000000853

SikaViscoFlow-1000-en-GB-(04-2019)-2-1.pdf

