

PRODUCT DATA SHEET

SikaRapid[®]-1

HARDENING ACCELERATING CONCRETE ADMIXTURE.

PRODUCT DESCRIPTION

SikaRapid[®]-1 is a liquid hardening accelerator for concrete and mortar. It meets the requirements for hardening accelerators according to EN 934-2. SikaRapid[®]-1 promotes early strength development without negatively influencing final strengths.

USES

SikaRapid[®]-1 is especially suitable for any application where fast early strength development plays a major role, or is of crucial importance within 6 to 24 hours. SikaRapid[®]-1 is used for the following applications:

- Precast concrete
- Ready- mixed concrete where early demoulding is essential
- Cold ambient temperatures to achieve sufficient strength gain
- Slip-formed concrete
- Ready- mixed concrete where minimum time delays are critical

CHARACTERISTICS / ADVANTAGES

SikaRapid[®]-1 provides the following advantages through accelerated hardening of the concrete:

- Faster turnaround of formwork in precast applications
- Reduced or eliminated heat or steam curing
- Fast construction processes and early load bearing capacity
- Continuous concreting at low temperatures
- No negative effects on the final strengths

When applied with a superplasticizer, SikaRapid[®]-1 will not change the fresh concrete properties produced by the superplasticizer.

SikaRapid[®]-1 does not contain chlorides or any other ingredients which promote the corrosion of steel. It is therefore suitable for use in reinforced concrete

APPROVALS / STANDARDS

Conforms to the requirements of EN 934-2, Table 7 DoP 02 14 02 02 100 0 000004 1088, certified by Factory Production Control Body 0086, Certificate 541325, and provided with the CE mark

PRODUCT INFORMATION

Chemical Base	Mixture of organic and inorganic complex agents.
Packaging	20 litre drum, 1000 litre IBC
Appearance / Colour	Red liquid
Shelf Life	12 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.
Storage Conditions	Storage at temperatures between 5 °C and 30 °C. Protect from direct sunlight, frost and contamination.
Density	~1.17 kg/l (at +23°C)
pH-Value	9.0 +/- 1.0
Viscosity	< 10 mPa s at +23°C

Total Chloride Ion Content < 0.01 M-% (chloride-free)

Equivalent Sodium Oxide < 10.0 M-%

TECHNICAL INFORMATION

Concreting guidance The standard rules of good concreting practice, concerning production and placing, are to be followed. Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components. Fresh concrete must be cured properly and curing applied as early as possible.

APPLICATION INFORMATION

Recommended Dosage 0.5 - 1.5 % by weight of cement

Dispensing SikaRapid®-1 is added to the gauging water or added with it into the concrete mixer.
SikaRapid®-1 may also be added into the ready-mix truck on site. When added on site the truck mixer shall rotate its drums at maximum revolutions for at least 1 minute per m³ concrete and a minimum of 5 minutes to achieve a uniform mix. The concrete has to be visually checked for uniform consistence before discharging.

Restrictions SikaRapid®-1 shall not be added to dry cement.

LIMITATIONS

When using SikaRapid®-1 a suitable mix design has to be produced and the local material sources shall always be trialled.

If frozen and/or if precipitation of the product has occurred, SikaRapid®-1 may be used after thawing slowly at room temperature and intensive mixing.

Before application, suitability tests must be performed.

It is advised against the application of SikaRapid®-1 in pre-tensioned pre-stressed concrete produced with the span bed method.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet
SikaRapid®-1
January 2019, Version 01.02
021402021000000004

SikaRapid-1-en-GB-(01-2019)-1-2.pdf

